

AQUATAC™ 6085 Dispersion

PRODUCT DATA SHEET

AQUATAC 6085 resin dispersion is a unique rosin ester dispersion for use in waterborne pressure sensitive adhesives. Formulations with AQUATAC 6085 will have aggressive tack and peel, as well as excellent shear properties.

FEATURES:

- High solids
- Improved tack and peel properties
- Outstanding shear properties
- AQUATAC 6085 dispersion contains 97% USDA certified biobased content

POTENTIAL APPLICATIONS:

- Pressure sensitive adhesives (PSA)
- Woodworking
- Flooring

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Solid Content (%)	AQCM 029	59.5-62.5	61
Viscosity (mPa.s)	AQCM 004	3000-8000	5342
pH	AQCM 035	6.0-8.0	7.4
Particle size (microns)	AQCM 173	Max. 2.5	0.7


*Kraton test methods are available upon request

TYPICAL VALUES

Property Base Resin	Test Method*	Typical Value
Softening Point (°C)	AQCM 003	82
Acid Number (mg KOH/g)	AQCM 001	10
Color, Gardner, neat	AQCM 002	5

*Kraton test methods are available upon request

COMPATIBILITY	AQUATAC™ 6085 resin dispersion is compatible with <ul style="list-style-type: none"> - Acrylics - Carboxylated SBR lattices - Natural Rubber lattices over a wide pH-range
PACKAGING	AQUATAC 6085 resin dispersion is delivered in drums, totes or bulk.
STORAGE RECOMMENDATION	AQUATAC 6085 resin dispersion is solvent-free and must be protected from freezing. In addition, all containers must be kept closed to prevent skin formation which would require filtering.



The USDA Certified Biobased Product label is a certification mark of the U.S. Department of Agriculture.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and AQUATAC are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2019-2022 Kraton Corporation

Contact us:
 Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com