

SYLVACLEAR™ 1370 Rosin Ester

PRELIMINARY DATA SHEET

SUBJECT TO CHANGE

SYLVACLEAR 1370 liquid rosin ester has a broad compatibility with rosin acids, other rosin esters, waxes, and ingredients typically used in depilatory waxes and cosmetics formulations. SYLVACLEAR 1370 can be used to optimize softening point and properties in depilatory waxes and cosmetics formulations.

FEATURES

- Liquid resin
- Broad compatibility
- Suitable to optimize softening points in depilatory waxes formulations
- SYLVACLEAR 1370 rosin ester contains 95% USDA certified biobased content


POTENTIAL APPLICATIONS

- Depilatory waxes
- Waterproof, no-transfer makeup products

PRELIMINARY SPECIFICATIONS

Property	Test Method*	Specification
Acid Number (mg KOH/g)	AQCM 001	Max 20
Viscosity, Brookfield, at 40 °C (mPa·s or cP)	AQCM 004	Max 6250

*Kraton test methods are available upon request



<p>COMPATIBILITY</p>	<p>SYLVACLEAR™ 1370 rosin ester is compatible with various types of waxes, polymers and oils, including:</p> <ul style="list-style-type: none"> - Beeswax - Paraffinic wax - Microcrystalline wax - Fischer-Tropsch wax - EVA Polymer - Mineral oil - Vegetable oil
<p>PACKAGING</p>	<p>SYLVACLEAR 1370 rosin ester is available in liquid form in drums, 190 kg net weight.</p>
<p>STORAGE RECOMMENDATION</p>	<p>It is recommended that SYLVACLEAR 1370 rosin ester be stored and transported dry and below 30°C / 86°F. Product stored or transported at higher temperatures should be evaluated for impact on performance before use.</p>



The USDA Certified Biobased Product label is a certification mark of the U.S. Department of Agriculture.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, **WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, SHELF-LIFE OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS.** The user assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo and SYLVACLEAR are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2021-2022 Kraton Corporation

Contact us:
 Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com