

SYLVALITE™ 2010 Rosin Ester

PRELIMINARY
PRODUCT DATA SHEET

SUBJECT TO CHANGE

SYLVALITE 2010 rosin ester tackifier is a low softening point ester of tall oil rosin with good stability and mild odor. This liquid tackifier has wide compatibility, potentially allowing it to be used in many adhesive systems, particularly where better wetting or low temperature tack is required.

FEATURES:

- Low softening point
- Extra light color
- Low odor
- Excellent stability
- SYLVALITE 2010 rosin ester contains 85% USDA certified biobased content

POTENTIAL APPLICATIONS:

- PSA tapes & labels
- Bookbinding
- Product Assembly
- Sealants
- Coatings
- Wax based products

SALES SPECIFICATIONS


Property	Test Method*	Specification
Color, Gardner, neat	AQCM 002	Max. 4
Acid Number (mg KOH/g)	AQCM 001	Max. 15
Viscosity, Brookfield at 45°C (cps.)	AQCM 004	2000 – 4000

*Kraton test methods are available upon request

Contact us:

Almere (NL): +31 (0)36 54 62 800
Savannah (US): + 1 (800) 526-5294
Shanghai (CN): + 86 21 6434 8898
www.kraton.com

<p>SOLUBILITY</p>	<p>SYLVALITE™ 2010 rosin ester is soluble in:</p> <ul style="list-style-type: none"> - Aromatic and aliphatic hydrocarbon solvents, like hexane and toluene - Esters and ketones, such as ethyl acetate and acetone - Long chain alcohols, such as butanol and pentanol - Chlorinated solvents
<p>COMPATIBILITY</p>	<p>SYLVALITE 2010 rosin ester is compatible with but not limited to:</p> <ul style="list-style-type: none"> - Ethylene Vinyl Acetate (EVA) - Ethylene n-Butyl Acrylate (EnBA) - Styrene-Isoprene-Styrene (SIS) - Styrene-Butadiene-Styrene (SBS) - SB Rubber - Natural rubber - Acrylic polymers
<p>PACKAGING</p>	<p>SYLVALITE 2010 rosin ester is available as viscous liquid in 55-gallon lined drums, 400 lb. net, or bulk molten material.</p>
<p>STORAGE RECOMMENDATION</p>	<p>It is recommended that SYLVALITE 2010 rosin ester be stored and transported dry and below 30°C / 86°F. Keep away from direct sun light or other sources of heat. Product stored or transported at higher temperatures should be evaluated for impact on performance before use.</p>



The USDA Certified Biobased Product label is a certification mark of the U.S. Department of Agriculture.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVALITE are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016-2021 Kraton Corporation

Contact us:
 Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (800) 526-5294
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com