

## SYLVALITE™ RE 85GB Rosin Ester

### PRODUCT DATA SHEET

SYLVALITE RE 85GB rosin ester is an ester of stabilized Tall Oil Rosin. This light colored product has been formulated to provide excellent heat and aging stability. When compounded in Ethylene Vinyl Acetate (EVA) hot melt adhesives, it provides excellent color stability when compared with other tackifiers of its type.

#### FEATURES:

- Light color
- Stable
- Low volatility at elevated temperatures
- Consistent performance
- SYLVALITE RE 85GB rosin ester contains 96% USDA certified biobased content

#### POTENTIAL APPLICATIONS:

- Packaging
- PSA tapes & labels
- Non-woven
- Flooring
- Sealants
- Coatings

### SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Softening Point (°C)	AQCM 003	83 - 87	84
Color, Gardner, neat	AQCM 002	Max. 5	3-
Acid Number (mg KOH/g)	AQCM 001	Max. 15	11

\*Kraton test methods are available upon request

### TYPICAL PROPERTIES


Property	Test Method*	Typical Value
Glass Transition Temperature (°C)	AQCM 218	35
Viscosity, Brookfield at 125°C (cps.)	AQCM 004	2700
Viscosity, Brookfield at 150°C (cps.)		325
Viscosity, Brookfield at 177°C (cps.)		80

\*Kraton test methods are available upon request

#### Contact us:

Almere (NL): +31 (0)36 54 62 800  
 Savannah (US): + 1 (912) 238-6439  
 Shanghai (CN): + 86 21 6434 8898  
[www.kraton.com](http://www.kraton.com)

<p><b>SOLUBILITY</b></p>	<p>SYLVALITE™ RE 85GB rosin ester is soluble in:</p> <ul style="list-style-type: none"> <li>- Aromatics and aliphatic hydrocarbon solvents, like hexane and toluene</li> <li>- Esters and ketones, such as ethyl acetate and acetone</li> <li>- Chlorinated solvents</li> <li>- Long chain alcohols, such as butanol and pentanol</li> </ul>
<p><b>COMPATIBILITY</b></p>	<p>SYLVALITE RE 85GB rosin ester is compatible with:</p> <ul style="list-style-type: none"> <li>- Ethylene Vinyl Acetate (EVA)</li> <li>- Ethylene Butyl Acrylate (EBA)</li> <li>- Styrene-Isoprene-Styrene (SIS)</li> <li>- Styrene-Butadiene-Styrene (SBS)</li> <li>- SB rubber</li> <li>- Natural rubber</li> <li>- Acrylic polymers</li> </ul>
<p><b>PACKAGING</b></p>	<p>SYLVALITE RE 85GB rosin ester is available in flaked form in multi-wall bags, 50 lb. net.</p>
<p><b>STORAGE RECOMMENDATION</b></p>	<p>It is recommended that SYLVALITE RE 85GB rosin ester be stored and transported dry and below 20°C / 70°F. To prevent remassing, keep away from direct sun light or other sources of heat. Product stored or transported at higher temperatures should be evaluated for impact on performance before use. Due to its low Tg, do not stack pallets on top of each other during storage. Mild remassing or compaction of the product that is readily broken apart is not considered a basis for rejection of the flaked product.</p>



The USDA Certified Biobased Product label is a certification mark of the U.S. Department of Agriculture.

**Disclaimer**

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVALITE are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2019-2022 Kraton Corporation

**Contact us:**  
 Almere (NL): +31 (0)36 54 62 800  
 Savannah (US): + 1 (912) 238-6439  
 Shanghai (CN): + 86 21 6434 8898  
[www.kraton.com](http://www.kraton.com)