

SYLVALITE™ RE 100L Rosin Ester

PRODUCT DATA SHEET

SYLVALITE RE 100L rosin ester is a stabilized pentaerythritol ester of Tall Oil Rosin. SYLVALITE RE 100L exhibits low color and good color stability. This resin is compatible with a broad range of polymers, which enables formulation flexibility in various hot melt and solvent based adhesive applications.

FEATURES:

- Provides good specific adhesion to a variety of substrates
- Light color
- Broad compatibility
- Low volatility at elevated temperatures
- Thermally stable
- High bio-based content (93%)

POTENTIAL APPLICATIONS:

- Packaging
- PSA tapes/labels
- Non-woven
- Flooring
- Woodworking
- Bookbinding
- Product Assembly

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Softening Point (°C)	AQCM 003	96 - 102	98
Color (Gardner, neat)	AQCM 002	Max. 5	4-
Acid Number (mg KOH/g)	AQCM 001	Max. 15	10

*Kraton test methods are available upon request

TYPICAL PROPERTIES

Property	Test Method*	Typical Value
Glass Transition Temperature (°C)	AQCM 218	48
Viscosity, Brookfield (125°C), cps.	AQCM 004	11800
Viscosity, Brookfield (150°C), cps.		955
Viscosity, Brookfield (177°C), cps.		150

*Kraton test methods are available upon request

Contact us:
 Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com

SOLUBILITY	<p>SYLVALITE RE 100L rosin ester is soluble in:</p> <ul style="list-style-type: none"> - Aromatic and aliphatic hydrocarbon solvents, like hexane and toluene - Esters and ketones, such as ethyl acetate and acetone - Long chain alcohols, such as butanol and pentanol
COMPATIBILITY	<p>SYLVALITE RE 100L rosin ester is compatible with:</p> <ul style="list-style-type: none"> - Ethylene Vinyl Acetate (EVA) - Ethylene Butyl Acrylate (EBA) - Styrene-Isoprene-Styrene (SIS) - Styrene-Butadiene-Styrene (SBS) - SB Rubber - Natural rubber - Acrylic polymers
PACKAGING	<p>SYLVALITE RE 100L rosin ester is available in flaked or pastille form in multi-wall bags, 50 lb. net or in bulk bags 2000 lb. net weight. It is also available as bulk molten material.</p>
STORAGE RECOMMENDATION	<p>It is recommended that SYLVALITE RE 100L rosin ester be stored and transported dry and below 30°C / 86°F. To prevent remassing, keep away from direct sun light or other sources of heat. Product stored or transported at higher temperatures should be evaluated for impact on performance before use.</p>



**PRODUCT
VIN-00002**

The product complies with the requirements described in Certification Scheme “bio-based content” (NCS 16785:2016-11) as confirmed by the certificate VIN-00002 of Vincotte nv. Validity of the certificate from 29 November 2016 until 29 November 2020.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVALITE are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016 Kraton Corporation.

Contact us:

Almere (NL): +31 (0)36 54 62 800
 Savannah (US): + 1 (912) 238-6439
 Shanghai (CN): + 86 21 6434 8898
www.kraton.com