

## SYLVAROS™ DRS 42 Disproportionated Rosin Soap

### PRODUCT DATA SHEET

SYLVAROS DRS 42 is a catalytically disproportionated tall oil rosin potassium soap. The disproportionation step converts Abietic Acid into the more oxidation resistant dehydroabietic acid isomer. The low Abietic Acid content minimalizes interaction with the catalyst-initiator system and does not influence the polymer chain length of the SBR rubber.

#### FEATURES

- Low Abietic Acid content

#### POTENTIAL APPLICATIONS

- Emulsifier in SBR Polymerization

### SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Acid Number(mgKOH/g)	AQCM 001	10 - 14	12
Total Solids %	AQCM 029	78 - 82	80
Abietic Acid %	AQCM 022	0.7 Maximum	0.4
Composition Chlorides, % NaCl	AQCM 027	0.2 Maximum	0.1

\*Kraton test methods are available upon request

### TYPICAL VALUES

Property	Test Method*	Typical Value
Dehydroabietic Acid %	AQCM 022	41
Viscosity cps 65°C	AQCM 004	1500
Viscosity cps 75°C	AQCM 004	800
Viscosity cps 80°C	AQCM 004	500

\*Kraton test methods are available upon request

<b>PACKAGING</b>	SYLVAROS™ DRS 42 disproportionated rosin soap is available as a hot solids paste in a tank car and a paste in lined open head 485 LB drums
<b>STORAGE RECOMMENDATION</b>	Drums – Unopened in a dry area below 25°C (77°F) out of direct sunlight. Bulk – Acid resistant stainless steel tank.

#### Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVAROS are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016-2018 Kraton Corporation

**Contact us:**  
Almere (NL): +31 (0)36 54 62 800  
Savannah (US): + 1 (912) 238-6439  
Shanghai (CN): + 86 21 6434 8898  
[www.kraton.com](http://www.kraton.com)