

SYLVAROS™ DRS 731 Disproportionated Rosin Soap

PRODUCT DATA
SHEET

SYLVAROS DRS 731 Disproportionated Rosin Soap is based on disproportionated rosin neutralized with sodium hydroxide solution. It can be used as emulsifier in the polymerization process of styrene-butadiene rubber, nitrile rubber, polychloroprene and acrylonitrile-butadiene-styrene plastics. SYLVAROS DRS 731 Disproportionated Rosin Soap is also suitable for the manufacture of pigments, and it can be used in the adhesive industry to enhance properties of adhesives on basis of casein or polymer emulsions.

FEATURES:

- Paste at room temperature
- Suitable for aqueous systems

POTENTIAL APPLICATIONS:

- Polymerization of synthetic rubber and plastics
- Pigments
- Adhesives

SALES SPECIFICATIONS

Property	Test Method*	Specification	Typical Value
Acid Number (mg KOH/g)	AQCM 001	10 – 12	11
Colour, US Rosin Standards	AQCM 062	WG or better	X
Solids (%)	AQCM 008	69 – 71	70
Unsaponifiables (%)	AQCM 011	Max 10	8
Abietic Acid by UV (%)	AQCM 212	Max 0.5	0.2
Dehydroabietic Acid by UV (%)	AQCM 212	Min 34	38
Chloride (%)	AQCM 229	Max 0.1	Not detectable
Iron (mg/kg)	AQCM 018	Max 10	3
Acid Number of Resin Component (mg KOH/g)	AQCM 228	150 – 170	159

*Kraton test methods are available upon request

TYPICAL PROPERTIES

Property	Test Method*	Typical Value
pH Value, 10% solution in water	AQCM 035	9

*Kraton test methods are available upon request

SOLUBILITY	SYLVAROS™ DRS 731 Disproportionated Rosin Soap is <u>soluble</u> in most organic solvents.
PACKAGING	SYLVAROS DRS 731 Disproportionated Rosin Soap is delivered in heated tank trucks, ISO containers or rail cars, or in steel or plastic drums (as available).
STORAGE RECOMMENDATION	SYLVAROS DRS 731 Disproportionated Rosin Soap is solvent-free and may therefore freeze if stored or transported at < 0 °C. Freezing does not affect the use of the product as chemical raw material, but the product must be fully homogenized after defrosting. Prior to usage product should be heated to 60 °C to facilitate handling. The storage tank should be equipped for homogenizing the product as it may separate during a longer period of storage. The content of IBC's and drums should also be homogenized prior to usage, unless full quantity of the container is used at once.

Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

KRATON, the KRATON logo, and SYLVAROS are trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2016-2019 Kraton Corporation