# KRATON

K697 North America 8/25/2020

Ellamera™ TER-SET 803

**Data Document** 

Identifier: K697DDa20NA

#### Description

Ellamera TER-SET 803 is a polymeric gellant for Personal Care formulations that is soluble in low polarity liquid carriers and oils, such as Isododecane and Paraffinum liquidum.

The product may find use as an ingredient in oil-based formulations in skin, sun and hair care, color cosmetics and fragrances.

Ellamera TER-SET 803 is manufactured in North America and supplied as an undusted white powder.

Sales Specifications						
Property	Test Method	<u>Units</u>	Sales Specification Range	Notes		
Polystyrene Content	KM 03	%m	29.5 TO 32.5	a		
Volatile Matter	KM 04	%m	<= 0.4			
Gel Content, on 100 mesh	BAM 906	ppmw	<= 50			
Color, Yellowness Index	BAM 1015		<= 4.0			
a Measured on the polyr	ner hefore hydrogenation					

Typical Properties (These are typical values and may not routinely be measured on finished product)							
Property	Test Method	<u>Units</u>	Typical Value	<u>Notes</u>			
Specific Gravity	ASTM D 792		0.91				
Dissolution Temperature	!	°C	110 - 130				

## Packaging

Ellamera Polymers are available in a number of different package types. For information specific to this grade, please contact your local Kraton Polymers representative.

## **End Use Requirements**

Ellamera products are meant for incorporation in finished articles intended for use in human contact areas. Manufacturers of the finished articles incorporating Ellamera products should observe all legal and regulatory requirements relevant to their finished articles. Some of these regulations require tests to be carried out on the finished article, e.g. migration. These are the responsibility of the finished article manufacturer. Regulatory information of individual Ellamera products is available from Kraton Polymers.

### Safety and Handling Precautions

Read the GHS Safety Data Sheet carefully and thoroughly before beginning any work. If you are unable to locate the GHS Safety Data Sheet from www.Ellamera.com, please contact the Product Safety support team at product.safety@kraton.com.

## **Legal Disclaimer**

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability

for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

#### For Further Information

**U.S.A Headquarters** Kraton Polymers U.S. LLC 15710 John F. Kennedy Blvd. Suite 300 Houston, Texas 77032 +1-800-4-KRATON (800-457-2866) info@kraton.com

Asia Pacific

Regional Headquarter/ Innovation Center Rm 2201, No.688, West Nan Jing Road 100 Century Avenue Shanghai, 200041, PR China +86 21 2082 3888 info.cn@kraton.com

**Europe, Middle East, Africa** Kraton Polymers Nederland B.V. Transistorstraat 16 NL - 1322 CE Almere The Netherlands +31 36 546 2846 info@kraton.com

Kraton, the Kraton logo, Ellamera, the Ellamera logo, RAD-THICK, BI-THIN, TER-SET and PER-SUST are trademarks or registered trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2020 Kraton Corporation