



K0017  
Europe  
2/24/2022

## KRATON™ D1192 A Polymer

Data Document

Identifier : K017DDm22E

### Description

Kraton D1192 A is a clear linear block copolymer based on styrene and butadiene with bound styrene of 30% mass. It is supplied from Europe in the physical forms described below:

- Kraton D1192 AT - supplied as porous pellets dusted with talc
- Kraton D1192 AS - supplied as porous pellets dusted with amorphous silica
- Kraton D1192 ASM - supplied as powder dusted with amorphous silica
- Kraton D1192 ATM - supplied as powder dusted with talc for the North American market

Kraton D1192 A is used for modification of industrial and paving bitumen. It may also be suitable for use in formulating adhesives, sealants and coatings, and in the modification of polymers.

### Sales Specifications

Property	Test Method	Units	Sales Specification Range	Notes
Vis, Sol (Toluene) 25.0%w @25C	KM 06	Pa.s	1.4 TO 2.4	
Molecular Weight	KM 01	kg/mol	138 TO 162	
Polystyrene Content	KM 03	%m	28.5 TO 32.5	
Vinyl Content	KM 03	%	≥ 35	
Triblock Content	KM 01	%	≥ 90	
Total Extractables	KM 05	%m	≤ 1.0	
Volatile Matter	KM 04	%m	≤ 0.3	
Antioxidant Content	KM 08	%m	≥ 0.16	a
Ash (AS, AT)	ISO 247	%m	0.1 TO 0.4	
Ash (ATM)	BAM 908	%w	4.0 TO 6.0	
Ash (ASM)	ISO 247	%m	2.5 TO 5.0	

**a** Non-staining phenolic antioxidant

### Typical Properties (These are typical values and may not routinely be measured on finished product)

Property	Test Method	Units	Typical Value	Notes
Hardness, Shore A (15 sec)	ASTM D 2240	Hardness, Shore A (15 sec)	70	a
Bulk Density	ASTM D 1895 method B	kg/dm <sup>3</sup>	0.4	
Specific Gravity	ISO 2781		0.94	
Melt Flow Rate, 200C/5kg	ISO 1133	g/10min.	< 1	
300% Modulus	ISO 37	MPa	4.8	
Elongation at Break	ISO 37	%	1000	
Tensile Strength	ISO 37	Mpa	33	

**a** Measured on compression molded slabs

### Packaging

Kraton Polymers are available in a number of different package types. For information specific to this grade, please contact your local Kraton Polymers representative.

KRATON and the Kraton logo are either trademarks or registered trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2022 Kraton Corporation



#### End Use Requirements

If the finished article is intended for use in food contact and packaging applications, toys, or human contact areas, manufacturers of the final product should observe all relevant regulations. Some of these regulations require tests to be carried out on the final product, e.g. migration. These are the responsibility of the final product manufacturer. Information on the food packaging clearances of individual products is available from Kraton Polymers.

#### Safety and Handling Precautions

Read the GHS Data Sheet carefully and thoroughly before beginning any work.

#### Legal Disclaimer

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

#### For Further Information

<b>U.S.A Headquarters</b> Kraton Polymers U.S. LLC 15710 John F. Kennedy Blvd. Suite 300 Houston, Texas 77032 +1-800-4-KRATON (800-457-2866) info@kraton.com	<b>Asia Pacific</b> Regional Headquarter/ Innovation Center Rm 2201, No.688, West Nan Jing Road 100 Century Avenue Shanghai, 200041, PR China +86 21 2082 3888 info.cn@kraton.com	<b>Europe, Middle East, Africa</b> Kraton Polymers Nederland B.V. Transistorstraat 16 NL - 1322 CE Almere The Netherlands +31 36 546 2846 info@kraton.com
--	--	---