



K0249  
North America  
1/25/2022

## KRATON™ D4150 K Polymer

Data Document

Identifier : K249DDm22U

### Description

Kraton D4150 K is a linear triblock copolymer based on styrene and butadiene with a polystyrene content of 31%. It is supplied from North America in the physical form identified below.

- Kraton D4150 KT - supplied as a dusted porous pellet
- Kraton D4150 KU - supplied as an undusted porous pellet

Kraton D4150 K is used as a modifier of bitumen and polymers. It is also suitable as an ingredient in formulating compounds for footwear applications, molded and extruded goods applications and may be used in formulating adhesives, sealants, and coatings.

### Sales Specifications

Property	Test Method	Units	Sales Specification Range	Notes
Polystyrene Content	KM 03	%m	29.0 TO 33.0	
Oil	KM 05	%m	32.3 TO 34.3	
Antioxidant	KM 08	%m	0.13 TO 0.35	
Volatile Matter	KM 04	%m	<= 0.7	
Ash, T	BAM 908	%w	0.25 TO 0.45	a

**a** Talc specification for D4150 KT

### Typical Properties (These are typical values and may not routinely be measured on finished product)

Property	Test Method	Units	Typical Value	Notes
300% Modulus	ASTM D-412	psi	160	c
Hardness	ASTM 2240	Shore A (10s)	45	b
Diblock content	n/a		17	
Melt Index 200°C, 5kg	n/a	gms/10 Min.	9.5	
Styrene / Rubber ratio	n/a		31/69	
Elongation at break	ASTM D-412	%	1400	c
Tensile strength	ASTM D-412	psi	2800	c
Solution Viscosity	BAM 922	cps	850	a
Specific Gravity	ASTM D 792		0.92	

**a** 25%w toluene solution at 25C  
**b** Typical values on polymer compression molded at 300F.  
**c** Measured on films cast from a solution in toluene.

### Packaging

Kraton Polymers are available in a number of different package types. For information specific to this grade, please contact your local Kraton Polymers representative.

KRATON and the Kraton logo are either trademarks or registered trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2022 Kraton Corporation



**End Use Requirements**

If the finished article is intended for use in food contact and packaging applications, toys, or human contact areas, manufacturers of the final product should observe all relevant regulations. Some of these regulations require tests to be carried out on the final product, e.g. migration. These are the responsibility of the final product manufacturer. Information on the food packaging clearances of individual products is available from Kraton Polymers.

**Safety and Handling Precautions**

Read the GHS Data Sheet carefully and thoroughly before beginning any work.

**Legal Disclaimer**

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

**For Further Information**

<b>U.S.A Headquarters</b> Kraton Polymers U.S. LLC 15710 John F. Kennedy Blvd. Suite 300 Houston, Texas 77032 +1-800-4-KRATON (800-457-2866) info@kraton.com	<b>Asia Pacific</b> Regional Headquarter/ Innovation Center Rm 2201, No.688, West Nan Jing Road 100 Century Avenue Shanghai, 200041, PR China +86 21 2082 3888 info.cn@kraton.com	<b>Europe, Middle East, Africa</b> Kraton Polymers Nederland B.V. Transistorstraat 16 NL - 1322 CE Almere The Netherlands +31 36 546 2846 info@kraton.com
--	--	---