



K0412  
Europe  
2/15/2023

## KRATON™ D1101 A Polymer

**Data Document**

Identifier : K412DDn23E

### Description

Kraton D1101 A polymer is a clear, linear block copolymer based on styrene and butadiene with bound styrene of 31% mass. It is supplied from Europe in the physical forms identified as follows in the grade nomenclature:

- D1101 AT - supplied as porous pellets dusted with talc
- D1101 AS - supplied as porous pellets dusted with amorphous silica
- D1101 AU - supplied as porous pellets undusted
- D1101 ASM - supplied as powder dusted with amorphous silica
- D1101 AIM - supplied as powder dusted with calcium carbonate for supply to the North American market

Kraton D1101 A polymer is used as a modifier of bitumen in roofing felt compounds, roads and pipe coating. It may also be suitable for use in formulating adhesives, sealants and coatings and in the modification of polymers.

### Sales Specifications

Property	Test Method	Units	Sales Specification Range	Notes
Polystyrene Content	KM 03	%m	30.0 TO 32.0	
Vis, Sol (Toluene) 25.0%w @25C	KM 06	Pa.s	3.0 TO 5.0	
Volatile Matter	KM 04	%m	≤ 0.3	
Total Extractables	KM 05	%m	≤ 1.0	
Antioxidant content	KM 08	%m	0.14 ≥ =	
Ash (AU)	ISO 247	%m	≤ 0.2	
Ash (AS)	ISO 247	%m	≤ 0.4	
Ash (AT)	ISO 247	%m	≤ 0.4	a
Ash (ASM)	ISO 247	%m	2.5 TO 5.0	b
Ash (AIM)	BAM 908	%w	4.0 TO 6.0	c

- a** for bulk deliveries ash content is < 0.5% m  
**b** Europe and South America  
**c** North America

### Typical Properties (These are typical values and may not routinely be measured on finished product)

Property	Test Method	Units	Typical Value	Notes
Specific Gravity	ISO 2781		0.94	
Bulk Density	ASTM D 1895 method B	kg/dm <sup>3</sup>	0.4	
Melt Flow Rate, 200°C/5kg	ISO 1133	g/10min.	< 1	
Tensile Strength	ISO 37	Mpa	33	b
300% Modulus	ISO 37	MPa	2.9	b
Elongation at Break	ISO 37	%	880	b
Hardness, Shore A (30 sec)	ISO 868	Hardness, Shore A (30 sec)	72	a

- a** Measured on compression moulded slabs  
**b** Measured on films cast from a solution in toluene

### Packaging

Kraton's products are available in a number of different package types. For information specific to this grade, please contact your local Kraton representative.

**End Use Requirements**

The end user of the product is solely responsible to comply with all regulatory and testing requirements applicable to the end use of the finished article incorporating the product.  
Information regarding the regulatory status of the product is available from Kraton on request.

**Safety and Handling Precautions**

Read the GHS Data Sheet carefully and thoroughly before handling and using the product. If you are unable to locate the GHS Safety Data Sheet from [www.kraton.com](http://www.kraton.com), please contact the Product Safety support team at [product.safety@kraton.com](mailto:product.safety@kraton.com).

**Legal Disclaimer**

We cannot anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their use do not infringe any intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HEREIN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, EXCEPT AS SET FORTH IN ANY APPLICABLE CONTRACT THAT MAY BE IN PLACE BETWEEN KRATON AND THE CUSTOMER OR, ABSENT SUCH A CONTRACT, KRATON'S TERMS AND CONDITIONS OF SALE. The end user assumes all responsibility and liability for loss or damage arising from the handling and use of Kraton's products, whether used alone or in combination with other products.

KRATON and the Kraton logo are either trademarks or registered trademarks of Kraton Corporation, or its subsidiaries or affiliates, in one or more, but not all countries.

©2023 Kraton Corporation

**For Further Information**

<b>U.S.A Headquarters</b> Kraton Corporation 15710 John F. Kennedy Blvd. Suite 300 Houston, Texas 77032 +1-800-4-KRATON (800-457-2866) <a href="mailto:info@kraton.com">info@kraton.com</a>	<b>Asia Pacific</b> Regional Headquarter/ Innovation Center Rm 2201, No.688, West Nan Jing Road Shanghai, 200041, PR China +86 21 2082 3888 <a href="mailto:info.cn@kraton.com">info.cn@kraton.com</a>	<b>Europe, Middle East, Africa</b> Kraton Polymers Nederland B.V. Transistorstraat 16 NL - 1322 CE Almere The Netherlands +31 36 546 2846 <a href="mailto:info@kraton.com">info@kraton.com</a>
---	--	--